

INJECTION MOLDING OF

MAGNUM™ ABS RESINS



TRINSEO™

TECHNICAL INFORMATION

Drying

Acrylonitrile butadiene styrene (ABS) Resins, along with other commercial polymers such as nylon, polycarbonate, acrylics, and thermoplastic urethanes, are hygroscopic, absorbing moisture and requiring drying before processing. However, unlike other resins that suffer the loss of physical properties, if water is not removed prior to processing, parts injection molded with ABS resins only suffer from poor surface aesthetics due to splay from the failure to adequately dry the resin. Splay results from the formation of tiny voids in the surface of the part created by water vapour and appearing as silver streaks on the part surface. ABS resin moisture should be less than 0.1 percent prior to injection molding to prevent surface defects.

Hot air desiccant bed dehumidifying hopper dryers are typically used. These dryers remove moisture from the process air to deliver hot, dry air with dew points as low as -40°C . Dew point readings of the air entering the hopper should be taken periodically to ensure that the desiccant is still effective and delivering air with a dew point less than -30°C . If measured dew point levels are greater than this, the desiccant should be regenerated or replaced.

Typical required air flow rates through the hopper dryer are one cubic foot per minute per pound of resin. Small lab scale samples are often adequately dried on flat trays in temperature controlled ovens prior to molding. The typical recommended drying conditions for ABS resins are a minimum of two hours at $80\text{--}90^{\circ}\text{C}$. However, pellet geometry and size and composition of the resin do affect the length of time to dry the resin to the recommended moisture level of 0.1 percent.

Melt Temperature

The ABS melt temperature should be between 220 and 275°C with an aim point of 230°C . The optimum temperature profile depends on many variables, such as machine capacity to shot size ratio, screw design, mold and part design and cycle time. Generally, barrel temperature controllers should be PID type and set so the material melts gradually, with cooler rear zone and hotter front zone temperatures. For vented barrel machines, a relatively flat temperature profile is recommended to ensure the polymer is melted by the time it reaches the vent zone. Reverse temperature profiles are used occasionally to compensate for improper screw design; to reduce machine amperage or torque requirements; and to compensate for machines with short let down (L/D) ratios.

Optimum melt temperature will depend on the particular ABS resin chosen as well as the part size, complexity, and desired surface appearance. Because machine set points and actual melt temperature often vary by as much as $\pm 25^{\circ}\text{C}$, actual

measurement of the melt temperature is recommended to verify that it falls within the recommended range. The suggested method for checking the melt temperature is to use a pyrometer with the probe heated to 15°C above the expected melt temperature. Insert the probe into the purge patty for 30 seconds, and record the melt temperature. Keeping a uniform melt temperature within the recommended range is essential to ensure good color matching of mating component parts.

A higher melt temperature reduces the viscosity of the material and allows the material to flow more easily. Melt temperatures in the upper end of the recommended range may be necessary when processing thin-wall parts, difficult-to-fill parts, parts with very small gates and parts with long flow lengths. Higher melt temperatures generally also produce parts with higher gloss. Excessive melt temperatures may result in thermal degradation and a loss of performance properties and aesthetics.

A lower melt temperature generally produces parts with lower gloss. Lower processing temperatures also reduce the risk of thermal degradation and shorten the necessary cooling time. However, excessively low melt temperatures may result in high residual molded-in stress.

Mold Temperature

Generally, cooling time is the rate determining factor for overall cycle time. To obtain the best part properties and consistent dimensional tolerances, uniform heat removal is critical. Using a mold temperature controller will minimize temperature variations. Recommended mold temperatures range from 25 to 60°C , depending on the ABS chosen.

For plating or painting applications, higher mold temperatures (above the recommended range) may be required to reduce the surface stresses and provide for better plate or paint adhesion. Cooling lines should be properly placed and spaced around the part for effective heat removal. The cooling lines should be adequately sized without restrictions in the connectors or associated piping. The flow rate of the cooling medium should be sufficient to provide for turbulent flow through the cooling lines. Cleanliness of the cooling medium should also be maintained to prevent blockage of the cooling lines.

Higher mold temperatures in the upper recommended range generally provide better surface finish, less molded-in stress because of slower cooling and easier filling of thin-wall parts and parts with long flow lengths. Lower mold temperatures allow the resin to set-up faster to reduce the overall cycle time. Lower mold temperatures will produce lower gloss levels, while higher mold temperatures will produce higher gloss levels.

Plasticising Conditions

Screw Speed

For optimum homogeneity of the polymer melt, slow screw speeds are generally recommended for ABS. Screw rotation should occur throughout the cooling cycle. This can best be accomplished by establishing a proper balance between screw speed and back pressure, that is, a ratio of speed and pressure that will allow plasticisation to continue throughout the entire cooling cycle. Screw speed should be adjusted with a minimal pause (less than 2 seconds) before mold opening.

Back Pressure

Recommended screw back pressures range from 10-35 Bar, assuming a nominal hydraulic intensifying ratio of 10:1. Back pressure is necessary to ensure uniformity of the polymer melt for maximum part performance. It is particularly important to use sufficient back pressure when coloring in-house with color concentrates. Operating at the upper end of the recommended range may be necessary to achieve good distributive mixing and uniform part color.

Injection Conditions

The injection molding process is generally divided into two stages. The first is injection or fill and the second is packing or hold. During the first stage, or filling stage, it is recommended that pressure is set near its maximum and the speed of the screw is controlled with velocity controls.

The machine will only use whatever pressure is necessary to move the ram at the set speed. This technique will help provide consistent parts because the cavity is filled at a uniform rate, despite differences in viscosity due to temperature fluctuations and other factors. It is very important to switch from first stage to second stage when the part is 95 to 98 percent full. Without a switch from first to second stage pressure before the cavity is full, the high pressure of the first stage pump will cause the part to flash and may cause damage to the mold.

It is recommended to switch from first stage to second stage based on the position of the ram or the cavity pressure. Switchover based on hydraulic pressure and time is recommended if ram position or cavity pressure controls are not available. While maintaining a cushion, second stage pressure should be set at the lowest level necessary to properly pack out the part to achieve the desired surface aesthetics. In general, packing pressure is lower than first stage pressure. Under-packing the part will result in excessive sink marks, poor dimensional tolerances and poor surface aesthetics. Over-packing will result in excessive molded-in stress, increased part weight and poor part performance.

Injection Speed

Injection speed depends on the particular part and machine. Since an erratic injection speed can cause a variety of part defects, a uniform injection speed is best. In general, moderate to fast injection speeds are recommended for high gloss ABS resins. High injection speeds will create high shear as the melt passes through the runners, gates and along the cavity surface. Because of the shear rate dependency of ABS, this will decrease the polymer viscosity, which allows the material to flow easier and helps fill thin-wall parts. However, excessive injection speed may result in flash, or thermal degradation due to shear heating. When using low gloss ABS resins, medium to slow injection speeds usually provide more uniform low gloss. Fast injection speeds may result in excessive gate blush and higher gloss levels.

Melt Cushion

The use of a "cushion," or residual polymer melt in the barrel after injection, will help ensure that the proper amount of material is injected into the cavity. During the packing phase, the material in the cavity is shrinking. To compensate for this shrinkage, additional material must be supplied to the cavity until gate freeze-off. A small melt cushion provides a ready source of additional melt to use during packing. If the screw is allowed to "bottom-out," the packing pressure cannot be transferred through the polymer to pack out the cavity. This will result in poor part consistency due to short shots, poor dimensional stability, excessive sink marks or poor aesthetics. It is generally recommended that a small cushion size be employed. This will minimise the residence time and heat history of the polymer, reducing the potential for polymer degradation.

Regrind

Trinseo's mass solution polymerisation process results in ABS resins with excellent thermal and processing stability. To the converter this means that there are few limitations to using regrind from MAGNUM™ ABS Resins, as long as normal material handling conditions have been observed. Some of our customers produce parts from 100 percent regrind MAGNUM™ ABS Resins, although the risk of contamination limits this practice to selected applications.

SUGGESTED INJECTION MOLDING CONDITIONS FOR MAGNUM™ ABS RESINS

If you have a specific application requirement or would like more information about MAGNUM™ ABS Resins, contact your Trinseo Specialist or visit www.trinseo.com.

Parameter	Value
Temperature (°C)	
Temperature	Low or normal gloss High heat or high gloss
Nozzle	230 245-290
Front	220 245-290
Intermediate	210 220-250
Rear (Hopper)	195-200 205-215
Mold Temperature	30-70 ⁽¹⁾ 50-70
Manifold Temperature	220-275 230-290
Melt Temperature (Air Shot)	220-275 230-90
Pressure (Bar)	
Back Pressure	10-35 (higher for self coloring)
Injection Pressure	Adjust to control part weight & dimensions
Hold/Pack Pressure	30-70
Clamp Force (Tonnes/cm ² Projected Area)	0.3-0.8
Drying	
Time (Hours) Excludes Warm-up time	2-4
Temperature (°C)	80-90
Maximum Moisture (%) (Equilibrium Level = 0.8%)	0.10
Rate	
Injection Speed	Adjust to control appearance
Ratios	
Screw Compression Ratio	2.0-3.0/1
Screw L/D Ratio	>20/1
Mold Shrinkage (%)	0.4-0.7

⁽¹⁾ Higher mold temperature will improve gloss for the low gloss grades

The principles of Responsible Care® and Sustainable Development influence the production of printed literature for Trinseo S.A. and its affiliated companies. As a contribution towards the protection of our environments, Trinseo's printed literature is produced in small quantities and on paper containing recovered/post-consumer fiber and using 100 percent soy-based ink whenever possible.

Product Stewardship

Trinseo and its affiliated companies have a fundamental concern for all who make, distribute, and use their products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products so that appropriate steps may be taken to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Trinseo products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Customers are responsible for reviewing their manufacturing processes and their applications of Trinseo products from the standpoint of human health and environmental quality to ensure that Trinseo products are not used in ways for which they are not suitable. Trinseo personnel are available to answer questions and to provide reasonable technical support. Trinseo product literature, including safety data sheets, should be consulted prior to the use of Trinseo products. Current safety data sheets are available from Trinseo. No freedom from infringement of any patent owned by Trinseo or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the customer is responsible for determining whether products and the information in this document are appropriate for the customer's use and for ensuring that the customer's workplace and disposal practices are in compliance with applicable legal requirements. Although the information herein is provided in good faith and was believed to be accurate when prepared, Trinseo assumes no obligation or liability for the information in this document.

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS

Trinseo requests that customers refer to Trinseo's Medical Application Policy <http://www.trinseo.com/medical.htm> before considering the use of Trinseo products in medical applications. The restrictions and disclaimers set forth in that policy are incorporated by reference.

DISCLAIMER

TRINSEO MAKES NO WARRANTIES, EITHER EXPRESS OR IMPLIED, IN THIS DOCUMENT; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE (INCLUDING MEDICAL APPLICATIONS) ARE EXPRESSLY EXCLUDED. TRINSEO DISCLAIMS ANY AND ALL LIABILITY FOR LOSSES OR DAMAGES THAT MAY RESULT FROM THE USE OF TRINSEO PRODUCTS IN UNSUPPORTED USE. TRINSEO MAKES NO WARRANTIES, EXPRESS OR IMPLIED, THAT THE USE OF ANY TRINSEO PRODUCT WILL BE FREE FROM ANY INFRINGEMENT CLAIMS.

GENERAL NOTICE

Any photographs of end-use applications in this document represent potential end-use applications but do not necessarily represent current commercial applications, nor do they represent an endorsement by Trinseo of the actual products. Further, these photographs are for illustration purposes only and do not reflect either an endorsement or sponsorship of any other manufacturer for a specific potential end-use product or application, or for Trinseo, or for specific products manufactured by Trinseo.

If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Trinseo to change specifications and/or discontinue production, and (4) although Trinseo may from time to time provide samples of such products, Trinseo is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

For additional information not covered by the content of this document or to ensure you have the latest version of this document available, please refer to the Customer Information Group contact information on our website at www.trinseo.com/contact/.

For more information on products, innovations, expertise, and other services available from Trinseo, visit www.trinseo.com, or contact us as indicated below.

North America	+1-855-TRINSEO (855-874-6736)
South America	
Brazil	+0800-0474714
Argentina	+0800-2660569
Chile	+1230-020-1124
Colombia	+01800-5182475
Mexico	+01800-0834913
Europe	+31-115-67-2601
Asia Pacific	+60-3-7965-5319
China	+86-21-3851-1017
Email	CIG@trinseo.com

www.trinseo.com